REPORT DOCUMENTATION PAGE AFRL-SR-BL-TR-01-					
Public reporting burden for this collection of information is estimated to average 1 hour per response including the time for reviewing instrudata needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other asp this burden to Department of Defense. Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0186 4302. Respondents should be aware that nowithstanding any other provisions of law, no person shall be subject to any penalty for failing to valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
valid OMB control number. PL 1. REPORT DATE (DD)	EASE DO NOT RETURN YOU	R FORM TO THE ABOVE ADDR 2. REPORT TYPE	RESS.		0261
12-02-2001	11	Technical			/1/97 - 7/31/2000
4. TITLE AND SUBTITLE 97 AASERT Experimental Studies of Mode Cour			oling and Prospe		CONTRACT NUMBER
		y Confined Micr		5b.	GRANT NUMBER
					9620-97-1-0466
				5c.	PROGRAM ELEMENT NUMBER
6. AUTHOR(S) Prof. Dennis G. Dep	pe			5d.	PROJECT NUMBER
•	•			5e.	TASK NUMBER
			,	5f.	WORK UNIT NUMBER
	ANIZATION NAME(S)	AND ADDRESS(ES)			PERFORMING ORGANIZATION REPORT NUMBER
The University Austin	of Texas at				
		AME(O) AND ADDRESS	(50)	10	SPONSOR/MONITOR'S ACRONYM(S)
	ce of Sponsore	AME(S) AND ADDRESS	(E2)	10.	SPONSOR MONTOR'S ACRON I M(S)
Projects	oroginode to eor	·u			
				11.	SPONSOR/MONITOR'S REPORT NUMBER(S)
12. DISTRIBUTION / AVAILABILITY STATEMENT Additional copies available from Prof. Dennis G. Deppe, The University of Texas at Austin					
		ولمناه		HIMPUNUE ()FF	CEOFSCIENTIFIC DESEASON (ACCORD)
1 The Control of the					
13. SUPPLEMENTARY NOTES AND DEEN REVIEWED AND DEALER FOR FUCUS ALL DE JAN AND 100-12. DISTRIBUTANTE DE					
14. ABSTRACT					
The abstract below is from the original proposal.					
polariton quantum ver confinement and ver QW-confined excito spatial extent). In microcavity optical	well (QW) light emi- tical confinement du on-polariton's unique principle, such an mode. The nearly i	tter. The microcavity te to GaAs/Al _X O ₃ dist to GaAs/Al _X O ₃ dist to feature as a radiation extended source is edual coupling allows	is a novel dielectric ributed Bragg reflecton in source of superradia pable of coupling in ovel studies of quar	e structure base ors (DBRs). The iance into the 100% of its sp ntum optics in	an optical mode coupled to an excitoned on both lateral native oxide (Al_XO_y) he interest in this system stems from the QW normal direction (due to its lateral ontaneous light emission into a planar semiconductor microcavities associated
with unity β, such as Rabi oscillations, ultralow threshold lasing, and generation of nonclassical light. In practice, however, the coupling					
from the exciton-polariton to the semiconductor microcavity is limited by dephasing either due to inhomogeneous broadening associated with QW width fluctuations, or homogeneous broadening arising from phonon and carrier-carrier scattering.					
15. SUBJECT TERMS Excitons, quantum dots, microcavity, Purcell effect					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION	18. NUMBER	19a. NAME OF RESPONSIBLE PERSON
			OF ABSTRACT	OF PAGES	Prof. Dennis G. Deppe
a. REPORT	b. ABSTRACT	c. THIS PAGE		6	19b. TELEPHONE NUMBER (include area code) (512) 471-4960

Standard Form 298 (Rev. 8-98) Prescribed by ANSI Std. Z39.18

AFOSR FINAL TECHNICAL REPORT

Project Title: 97-AASERT Experimental Studies of Mode Coupling and Prospects for Lasing in 3-Dimensionally Confined Microcavities

Grant No. F49620-97-1-0466

Period: August 1, 1997 - July 31, 2000

Dennis G. Deppe, Principal Investigator

Microelectronics Research Center The University of Texas at Austin Austin, Texas 78712

AFOSR Progress Report August 1, 1997 - July 31, 2000

Project Title: 97-AASERT Experimental Studies of Mode Coupling and

Prospects for Lasing in 3-Dimensionally Confined

Microcavities

Grant No.: F49620-976-1-0466

P.I.: D.G. Deppe, The University of Texas at Austin

2. Objectives:

This research program focuses on understanding the mode coupling due to excitons and other low dimensional electronic emitters in 3-dimensionally confined microcavities. We initially focused on excitons that can be excited in InGaAs/GaAs quantum wells, since there has been substantial interest in this system. However, from our initial studies we now believe that for room temperature experiments this system will inevitably suffer from thermal dephasing. The loss of coherence destroys the strong coupling to an optical microcavity.

On the other hand, excitons can also be realized in quantum dots (QDs). Due to the 3-dimensional electronic quantum confinement, excitons can be readily excited at room temperature, although the coherence properties of this system at high temperatures has not been (to our knowledge) investigated. However, to realize significant room temperature cavity effects the QDs appear to us to be a necessity.

We point out that the optical coupling of a QD exciton to a planar cavity is less than that for a quantum well. But ultimately the largest cavity effects are expected due to 3-dimensional optical confinement, discussed further below. Our work has been to show the microcavity effect due to the oxide-apertured microcavity, using both planar quantum well and quantum dot ϵ xcitons, and to obtain lasing from these excitons.

3. Status of effort:

In the first year we demonstrated exciton coupling to an oxide/GaAs planar cavity, with Rabi splitting observed for temperatures near room temperature. The results are described in the publication of Ref. [1] given below. This work uses oxide/GaAs distributed Bragg reflectors (DBRs), and the high contrast DBRs allows the polariton response, measured as a spectral splitting in the transmission characteristics, to be achieved even close to room temperature. A similar demonstration has been made from Prof. Hyatt Gibbs group from Arizona (published also published in APL).

Today we have much more impressive results in demonstrating cavity controlled spontaneous emission due to a 3-dimensionally confined microcavity. From a sequence of growth experiments we have developed InGaAlAs/GaAs QDs that emit at ~0.98 µm wavelength. Si APD photon counting modules can then be used to characterize the time resolved photoluminescence. The crystal growth is described in Refs. [2] and [3], which is partially supported by the DARPA Ultraphotonics Program. These QDs have been grown within semiconductor microcavities, and we have characterized how dielectrically apertured microcavities impact the spontaneous lifetime. At low temperature the QDs are spectrally and spatially decoupled, so that they radiate nearly independently. With inhomogeneous

broadening, each QD couples to the cavity with a dependence due to its own frequency of emission. Therefore, cavity effects can be determined simply by measuring the decay rate from the cavity-confined QDs for different frequencies.

We have obtained lasing in oxide-apertured VCSELs based on the QDs, but not really at the level of interest for this program. Most interesting would be to obtain lasing on the planar quantum well exciton or with a single QD. On the other hand, we have gained a great deal of knowledge of how QDs, especially, behave in a microcavity. We have demonstrated the first cavity controlled lifetimes based on the Purcell effect in this type of microcavity, reported in references [4]-[6] below. We believe that these devices will be the precursors to new types of high efficiency, high speed light emitting diodes and lasers. In related work we have shown how the Purcell effect can increase the modulation speed of microcavity lasers.

We are now applying the knowledge we have learned on this program to designs of single QD microcavity devices. This work is being performed both as stand-alone experiments in our UT laboratory and in collaborative experiments with Profs. Hyatt Gibbs and Galina Khitrova from the University of Arizona and Prof. Axel Scherer from the California Institute of Technology. We believe that with novel types of QDs designed for short radiative lifetimes and high gain that single QD lasing may be possible.

4. New Findings

The new demonstrations from this program are described references [4]-[6]. We have shown that the Purcell effect can be observed using self-organized QDs placed in dielectrically apertured microcavities. This device scheme opens up new possibilities for high efficiency, high speed, low power light emitters. Our group continues to be on the forefront in developing these types of devices.

5. Personnel Supported

1.) Luke A. Graham, Graduate Research Assistant, now at Picolight, Inc.

6. Publications

- [1] L.A. Graham, Q. Deng, D.G. Deppe, and D.L. Huffaker, "Exciton Spectral Splitting Near Room Temperature From High Contrast Semiconductor Microcavities," Appl. Phys. Lett. 70, 814 (1997).
- [2] O. Baklenov, D.L. Huffaker, A. Anselm, D.G. Deppe, and B.G. Streetman, "Influence of Al content on formation of InAlGaAs quantum dots grown by molecular beam epitaxy," J. Appl. Phys. 82, 6362 (1997).
- [3] D.L. Huffaker, L.A. Graham, and D.G. Deppe, "Ultra-Narrow Electroluminescence Spectrum From the Ground State of an Ensemble of Self-Organized Quantum Dots," Appl. Phys. Lett. 72, 214 (1998).
- [4] L.A. Graham, D.L. Huffaker, Q. Deng, and D.G. Deppe, "Controlled spontaneous lifetime in microcavity confined InGaAlAs/GaAs quantum dots," Appl. Phys. Lett. 72, 1670 (1998).
- [5] L.A. Graham, D.L. Huffaker, S.M. Csutak, Q. Deng, and D.G. Deppe, "Spontaneous Lifetime Control For Quantum Dot Light Emitters in Dielectrically-Apertured Fabry-Perot Microcavities," J. Appl. Phys. 85, 3383-3385 (15 March, 1999).

[6] L.A. Graham, D.L. Huffaker, and D.G. Deppe, "Spontaneous Lifetime Control in a Native-Oxide-Apertured-Microcavity," Appl. Phys. Lett. 74, 2408-2410 (26 April, 1999).

7. Interactions/Transitions:

- a. Participation/presentations at meetings:
- [1] (Invited) D.G. Deppe, D.L. Huffaker, L.A. Graham, and Q. Deng, "Oxide Microcavities," Optical Society of America Topical Meeting on Radiative Processes and Dephasing in Semiconductors, February 2-4, 1998, Coeur d'Alene, Idaho.
- [2] L.A. Graham, D.L. Huffaker, and D.G. Deppe, "Controlled Spontaneous Lifetime From Quantum Dots Confined in Microcavities," 40th Electronic Materials Conference, Technical Program, June 24-26, 1998, Charlottesville, VA, pg. 32.
- [3] D.L. Huffaker, L.A. Graham, and D.G. Deppe, "Ultra-Narrow Electroluminescence Spectrum From the Ground State of an Ensemble of Self-Organized Quantum Dots," Optical Society of America Topical Meeting on Radiative Processes and Dephasing in Semiconductors, February 2-4, 1998, Coeur d'Alene, Idaho.
- [4] D.L. Huffaker, L.A. Graham, and D.G. Deppe, "Carrier Confinement in InGa(Al)As Tunnel Coupled Quantum Dot Light Emitters Based on Ultra Small Apertures," Conference on Lasers and Electro-Optics, May 5-7, 1998, San Francisco.
- [5] L.A. Graham, D.L. Huffaker, and D.G. Deppe, "Controlled Spontaneous Lifetime From Quantum Dots Confined in Microcavities," 40th Electronic Materials Conference, Technical Program, June 24-26, 1998, Charlottesville, VA, pg. 32.
 - Presented in seminars at the Optical Science Center, University of Arizona, at the invitation of Hyatt Gibbs, and the Electrical and Computer Engineering Department, University of Michigan, at the invitation of Pallab Bhattach ya that included findings reported above.
- b. Consultative and advisory functions: None.
- c. Transitions: None
- 8. New Discoveries, inventions, patent disclosures: We have succeeded in the first clear demonstration of cavity controlled spontaneous lifetime in dielectrically-apertured 3-dimensionally confined microcavites. This work has been presented at the conferences listed above, and in journals [4]-[6]. Other groups have now demonstrated similar effects in etched-pillar Fabry-Perot microcavities and microdisk microcavities. All these demonstrations are based on exciton confined quantum dots.
- **9. Honors/Awards:** D.G. Deppe, Optical Society of America Nicholas Holonyak Jr. Award (1999) for the development of the oxide-confined vertical-cavity surface-emitting laser.